

Standox Reaktiv-Haftprimer Etching Adhesion Primer

- Transparent 2K acid primer
- Excellent adhesion
- Chromate-free
- For 3-stage systems
- Outstanding corrosion protection

Technical Description:

- Mix 1:1 with Standox Etching Adhesion Activator
- Potlife 8h / 18-22°C
- 2 spray passes = 8 micron
- Flash off 30 min / 18-22°C

SX-GB Version 04 312 1/3

Standox Reaktiv-Haftprimer

Substrate:

- Bare metal, sanded
- Aluminium, sanded
- Galvanised metal, sanded
- Through-hardened sanded paintwork

Pretreatment / Cleaning:



For substrate preparation information see Standox Painting System S1.



Use air fed respirator. Refer to relevant Health and Safety Data Sheets.

Application:



1:1 with Standox Etching Adhesion Activator Potlife 8-10 h / 18-22°C



Compliant 1.3 - 1.4 mm 2.0 - 2.5 bar inlet pressure2 = 8 - 10 micron



HVLP 1.3 - 1.6 mm

0.7 bar atomization pressure

2 = 8 - 10 micron



30 min / 18-22°C



Standox VOC / 2K Filler

SX-GB Version 04 312 2/3

Standox Reaktiv-Haftprimer

Flash point:

• 24°C / 75.2°F

Specific Gravity:

• 0.98 g/cm^3

Solid Content

(without thinner added):

- 29.2 Weight %
- 16.7 Volume %

VOC (2004/42/EC):

2004/42/IIB(c)(780)780 The EU limit value for this product (productcategory IIB.c) in ready to use form is max 780 g/l VOC. The VOC content of this product in ready for use form is max. 780 g/l.

Theoretical Coverage:

• 9,9 m²/l at 8 micron dry film thickness

Cleaning of equipment:

Clean after use with Standox Cleaning Thinner.

Important remarks:

- Standox Etching Adhesion Primer must be applied in combination with Standox VOC / 2K Filler in a 3-stage system.
- Do not overcoat with PE, EP, Standohyd and Standoblue products.

For professional use only. The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

SX-GB Version 04 312 3/3 Standox GmbH Postfach D-42271 Wuppertal